



## HIGH ALUMINA BRICK LZ-55

### Physical and chemical index

Item:	LZ-55	
Al <sub>2</sub> O <sub>3</sub> %	≥55	
Apparent porosity %	≤22	
Cold crushing strength Mpa	≥44.1	
Refractoriness °C	≥1770	
Refractoriness under loadin 0.2MPa	≥1450	
Permanent linear change	1500 °C ×2h	-0.4~0.1
	1450 °C ×2h	-