



HIGH ALUMINA BRICK LZ-65

Physical and chemical index

Item:	LZ-65	
Al ₂ O ₃ %	≥65	
Apparent porosity %	≤23	
Cold crushing strength Mpa	≥49	
Refractoriness °c	≥1790	
Refractoriness under loadin 0.2MPa	≥1500	
Permanent linear change	1500 °c ×2h	-0.4~0.1
	1450 °c ×2h	-